



Red Crocodile

Tile Adhesive



Tile adhesive with extra bonding

Red Crocodile Tile Adhesive is composed of Portland cement, sand, and special chemical additives, which lead to high adhesion strength for both wall and floor tiling, even without tile pre-soaking. Red Crocodile produces an excellent bond with greater coverage than conventional dry-set mortars for the installation of large sizes of ceramic tile, granite, marble, natural stones, and low-absorption tiles. It can also be applied in swimming pools.

Product features

- Perfect for ceramic and terracotta tile applied in swimming pool.
- Great for large size of porcelain tile interior floor and wall installation. Exterior is used only for floor.
- Suitable for marble, granite and natural stone tile installation.

USA Standard : ANSI A118.1, A118.4

Thai Industrial Standard : TIS 2703-2566 (2023) (General Quality Class)

Color : Grey / White

Installation

Preparation

For new substrate : The surface must be dry, flat, level and fully cured. It should be free of all grease, oil, dust, curing compounds, old adhesive residues and any other adulterant. Make sure water absorption of the substrate is at normal level. In case of new rendering or leveling, the substrate should be fully cured for 7 days or 168 hours per 1 cm thickness of adhesive before tiling.

For old substrate : Clean up the surface with high-pressure jet spray to remove dust, adulterant and any de-bonding tiles. Allow the substrate to dry completely before re-tiling

Proportion of Mixing

Red Crocodile Tile Adhesive 20 kg (per bag) per 5.60 L of water.

Red Crocodile Tile Adhesive 25 kg (per bag) per 7 L of water.

Red Crocodile Tile Adhesive 2.6 parts per 1 part of water by volume.



Mixing

- Mix Tile Adhesive with clean, potable water thoroughly until smooth with a mechanical mixer at a low speed (≤ 150 rpm).
- Let mortar slakes for 15 minutes before mixing a second time. Do not add water, latex, or additional powder after slaking period.

Application

1. Spread mortar with flat side of trowel to key-in substrate, and then apply additional mortar to ensure that it covers 100% at the back of tile.
2. Apply notched side at 60-degree angle in the same direction throughout installation surface.
3. Recommend applying the product all over the back of tile to compensate bending, prevent gap under tile that may cause less compressive strength and easily to crack.
4. After placing tile on the prepared surface, slide it orthogonally to the notched lines and tap to maximize bonding.
5. Tiles can be adjusted for proper alignment within 15 minutes after applying the products. Timing may vary depending on temperature. Recommend not to adjust further after setting. Make sure that the products are covered all over the back of tiles. Suitable thickness of tile adhesive on substrate is 2-10 mm

Curing and Grouting

- A minimum cure is obtained in 24-48 hours, depending on ambient temperatures.
- For better quality, Crocodile Tile Grout should be chosen to suit each type of tiles. Crocodile Tile Grout has many types and colors for each joint and places

Information

Density	1.54 g/cm ³
Open time	20 minutes
Slake time	15 minutes
Pot life at 23 \pm 2 °C	6 hours
Adjustment time	15 minutes
Suitable thickness of tile adhesive on substrate	2-10 mm
A minimum cure is obtained	24-48 hours

Remarks : Test results obtained from laboratories under controlled conditions may result in testing results that differ from the actual site conditions due to many factors such as temperature, environment, equipment, and others.



Technical Data

USA Standard

Test Method by USA Standard (American National Standard Institute)	ANSI A118.4	Standard Requirements A118.4	Result
Tensile adhesion strength	Part 5.3		
Open time : tensile adhesion strength 20 minutes at 28 days	Part 5.3	≥ 75 psi	> 75 psi
Shear strength (Porcelain mosaic)	Part 7.2		
1 day	Part 7.2.2	> 75 psi	> 100 psi
7 days	Part 7.2.3	> 200 psi	> 275 psi
7 days water immersion	Part 7.2.4	> 150 psi	> 175 psi
28 days	Part 7.2.5	> 200 psi	> 325 psi
12 weeks	Part 7.2.7	> 200 psi	> 325 psi

Remark : 1 MPa = 1 N/mm² = 10.197 ksc = 145.038 psi

Suggestion

- Grouting after tile installation at least 48 hours to achieve maximum efficiency.
- Recommend to apply the product all over the back of tile to maximize bonding strength.

Limitations

- Do not use tile adhesive with wood, asphalt, plastic coat or PVC, metal and mirror. (Do not allow frost within 72 hours)
- not recommend for resin or glass mosaic

** Please contact us for application on exceptional materials.

Caution

- May be harmful to the eyes, skin, or lungs. Wear suitable protective clothing, gloves, and eye/face protection.
- In case of contact with eyes, rinse immediately with water and seek medical advice.
- After contact with skin, wash immediately with water.
- Keep out of reach of children.
- Do not eat.

Storage

- It should be kept in a dry place and the temperature is not too high to avoid product's degradation.
- Use within 1 year from the date of manufacturing.



Packing

Net weight : 20 kg, 25 kg / Bag

The information provided is given in good faith, based on current knowledge and Jorakay Corporation's experience with the products when they are properly stored, handled and applied in normal situations and in accordance with the recommendations of Jorakay Corporation. This is useful for information and consulting but is not legally binding. In particular, it does not exempt the user from testing and verifying the suitability of the product for the desired application and purpose. Jorakay Corporation reserves the right to modifications that improve the product or its application. This version invalidates the previous ones.