

Crocodile Protectcrete Mortar

Structure Repairing



Crystalline Repairing Cement

Crocodile Protectcrete Mortar consists of cement, graded sand and special chemicals which is simple to use for repairing crack, joint and honeycomb in concrete with crystallization reaction which improve water seepage, pressure bearing and setting under submerged condition. High compressive strength, abrasion, and freezing-thaw durability. Crocodile Protectcrete Mortar can be used for repairing work before waterproofing layer, general repair, reglet installation, concave pressure-bearing joint, construction joint, crack, and honeycomb defects.

Product Features

- Can be applied in a very thin layer
- Setting under damp or submerged conditions
- Easy to use, just mix with water
- Abrasion resistance
- Inorganic compound without polymer admixture
- Good water pressure bearing
- Freeze thaw resistance

Color: Grey

Application Instruction

Substrate Preparation

- Clean the surface thoroughly, removing dirt, oil, paint, and concrete fragments
- In case of smooth, polished, or covered with finishing, scraping the surface for rough surface texture
- For crack repair, the crack needs to be widened and deepen for at least 20 mm
- Keep the surface saturated with water before applying the product



Mixing Ratio

- Crocodile Protectcrete Mortar 5 kg per 0.8 liter of water
- Crocodile Protectcrete Mortar 4.5 parts per 1 part of water

Mixing

- Mix Crocodile Protectcrete Mortar with water at recommended mixing ratio until the mixture started to thicken
- Mix in small quantity for 30 minutes of working period
- Do not add water to the mixture afterward

Application

1. After surface preparation, prime the surface with Crocodile Perfect Shield (Slurry coat)
2. Apply the mixture to fix defects while Crocodile Perfect Shield is still in damp condition, not over 6 hours
3. For thickness over 30 mm apply the mixture in layers under 30 mm
4. Left to dry for 1-2 hours then reapplying Crocodile Perfect Shield on the specimen

Usage Ratio

25 x 25 mm crack defect of 1 meter in length per 1.3 kg

Technical Data

Test Method	Standard	Evaluation
Density	-	1.25 kg/L
Compressive Strength	ASTM C109	
1 Day		270 ksc
3 Days		300 ksc
7 Days		370 ksc
28 Days		485 ksc

Remark : 1 Mpa = 1 N/mm² $\approx$ 10.2 ksc = 145.038 psi

Caution

- The product contains Portland cement and other admixture which may cause skin irritation. Using rubber gloves, dust masks, eye protection, and other safety equipment is recommended
- If in contact with eyes or face, rinse immediately and repeatedly with water, and then consult doctor immediately
- Keep away from children

**Storage**

- It should be kept in a dry place and the temperature is not too high.
- Shelf life for 1 year since manufactured date.

Packing

Net weight : 20 kg/pail, 5 kg/pail

The information provided is given in good faith, based on current knowledge and Jorakay Corporation's experience with the products when they are properly stored, handled and applied in normal situations and in accordance with the recommendations of Jorakay Corporation. This is useful for information and consulting, but is not legally binding. In particular, it does not exempt the user from testing and verifying the suitability of the product for the desired application and purpose. Jorakay Corporation reserves the right to modifications that improve the product or its application. This version invalidates previous ones.